



# Standard Test Method for Conducting Exterior Exposure Tests of Finishes for Thermal Insulation<sup>1</sup>

This standard is issued under the fixed designation C 488; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers out-of-doors exposure testing of finishes that are normally field-applied to thermal insulation which may include joints or joint sealants, or both. Such exposure may be essential prior to the determination of certain physical properties. This test method may also indicate compatibility problems between the joint sealant and the finish as well as the ability of the finish to span a dry joint. This test method is not intended to evaluate mildew resistance, efflorescence, or chemical resistance.

NOTE 1—For testing free plastic films, see Practice D 1435.

1.2 This test method does not prescribe the method of application, test duration, or inspection intervals.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are provided for information only.

## 2. Referenced Documents

### 2.1 ASTM Standards:

C 168 Terminology Relating to Thermal Insulating Materials<sup>2</sup>

D 1435 Practice for Outdoor Weathering of Plastics<sup>3</sup>

## 3. Terminology

3.1 *Definitions:* Terminology C 168 applies to the terms used in this test method.

## 4. Summary of Test Method

4.1 This test method specifies out-of-doors exposure, under ambient conditions, of field-applied finishes on thermal insulations, utilizing a minimum of three test specimens and one control specimen stored indoors.

## 5. Significance and Use

5.1 Both physical and chemical changes may occur from weather exposure, and these changes affect performance properties, service life, and maintenance schedules. For this reason, tests of properties relating to performance should be made both before and after specific periods of outdoor exposure.

5.2 This test method recognizes that differing geographical locations, environmental conditions, differences between surface temperatures and ambient temperatures, and test durations may have extremely varied effects upon the test results.

5.3 This test method is to be used for comparative qualitative testing.

## 6. Test Specimens

6.1 A minimum of three test specimens and one control specimen, each having been applied to an insulation base of minimum dimensions 1 by 6 by 12 in. (25 by 150 by 300 mm), shall be prepared. Insulation shall be the same as that which is proposed for the application. The control specimen shall be stored indoors.

6.2 The following types of specimens may be prepared:

6.2.1 Thermal insulation with no joints,

6.2.2 Thermal insulation with dry joints, and

6.2.3 Thermal insulation with joints filled with joint sealant.

6.3 For testing compatibility of sealants with finishes, joints at least 1 in. (25 mm) deep by  $\frac{1}{16}$  to  $\frac{3}{16}$  in. (2 to 5 mm) wide by 12 in. (300 mm) long may be cut in the insulation block. Joints shall be at least 4 in. (100 mm) apart and at least 4 in. (100 mm) from the edges, parallel to the joint. More than one sealant may be tested with a single finish by varying the sealant in each successive joint. These individual insulation pieces may be adhered with a suitable adhesive to a larger slab of the same insulation of dimensions of the desired completed specimen size in order to form a stable base for the specimen.

6.4 The joints filled with the joint sealant may have the finish applied immediately or allowed to cure or set for a week. The compatibility results may vary significantly depending upon how long the joint sealant is exposed to the atmosphere before the finish coat is applied.

6.5 The finish to be evaluated shall be applied to the specified test face and edges of the insulation base material. The application procedure for single and multiple coats shall be made a part of the test records.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee C-16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33 on Thermal Insulation Finishes and Vapor Transmission.

Current edition approved Dec. 30, 1983. Published May 1984. Originally published as C 488-62 T. Last previous edition C 488-79.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.06.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 08.01.

6.6 The thickness of the finish shall be made a part of the test record.

6.7 The specimen shall be prepared, flashed or sealed, and mounted so that liquid water cannot enter the specimen.

6.8 The use of any reinforcing membrane shall be made a part of the test record.

## 7. Procedure

7.1 The exposure or mounting position of the out-of-doors test specimens shall be 45° from the horizontal, facing upward and due south. The 6-in. (150-mm) dimension shall be horizontal, east to west.

7.2 Record the geographical latitude, longitude, and altitude of the test location.

7.3 Mount the test specimens so that they are neither in a shadow nor cast shadows on each other, and in such a manner that any products of weathering and rain water drippings shall not flow from one test specimen to another. Fasten specimens by the back surface in such a manner as to prevent displacement by the wind.

7.4 The test period shall be either as specified or sufficient to evaluate the characteristics of the finishes under evaluation.

7.5 Make inspections at regular intervals, observing:

7.5.1 Discoloration,

7.5.2 Cracking,

7.5.3 Crazeing,

7.5.4 Flaking,

7.5.5 Chalking,

7.5.6 Shrinkage,

7.5.7 Blistering,

7.5.8 Holes,

7.5.9 Loss of adhesion, and

7.5.10 Incompatibility between sealant and finish.

## 8. Report

8.1 Report the following information:

8.1.1 Type of insulation,

8.1.2 Size of sample,

8.1.3 Presence of joints,

8.1.4 Type and identification of joint sealants,

8.1.5 Length of cure time of joint sealants prior to application of finish,

8.1.6 Type of finish and color,

8.1.7 Application procedure for single and multiple coats,

8.1.8 Use of any reinforcing membrane,

8.1.9 Thickness of finish,

8.1.10 Geographical location (latitude, longitude, and altitude),

8.1.11 Test duration and dates of exposure and removal, and

8.1.12 Inspection intervals.

8.2 Report the following observations:

8.2.1 Discoloration,

8.2.2 Cracking,

8.2.3 Crazeing,

8.2.4 Flaking,

8.2.5 Chalking,

8.2.6 Shrinkage,

8.2.7 Blistering,

8.2.8 Holes,

8.2.9 Loss of adhesion, and

8.2.10 Incompatibility between sealant and finish.

## 9. Precision and Bias

9.1 No statement is made about either the precision or bias of this test method since the result merely reports the visual presence of discoloration, cracking, crazeing, flaking, chalking, shrinkage, blistering, holes, loss of adhesion, and incompatibility between sealant and finish.

## 10. Keywords

10.1 coatings; exterior exposure test; test procedure; vapor barrier finishes

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*